

FLY ASH



PARAMETERS	SPECIFICATION
Physical Characteristics (%)	
Fitness retained on 325 mesh (45 μ)	12.0 % max
Chemical Characteristics (%)	
Lose on Ignition	2.0% max
Moisture	0.5 % max
$\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{Fe}_2\text{O}_3$	70.0 % min
Sodium Oxide as Na_2O	1.5 % max
Sulfur tri Oxide as SO_3	2.0 % max
Chloride as Cl	0.1 % max