

# Copper Slag



PARAMETERS	SPECIFICATION
Gravity	3.56
Moisture	<0.001
Hardness	8 / moh's
Chloride	< 25 ppm
SiO <sub>2</sub>	31.83%
Fe <sub>2</sub> O <sub>3</sub> / Al <sub>2</sub> O <sub>3</sub>	55.77% / 2.82%
CaO	0.33 %
MgO	2.75%
TiO <sub>2</sub>	0.07%
Packing	25 KG in 1 Ton Bag / 2 Ton Bulk Bag
Applications	Surface blast-cleaning / Abbrasive blasting / Cement Industry